



**AMES
GOLDSMITH**
Corp.

ELECTRONIC MATERIALS


Silver Powder Type LCP-6

GENERAL DESCRIPTION
Part of the LCP Series Powders.

APPLICATIONS
Powder Metallurgical.

TYPICAL PROPERTIES

Physical Data:		Particle Size Distribution:
Tap Density:	2.0 - 3.0 g/cm ³	NT
Scott Density:	23 - 30 g/in ³	
Surface Area:	0.1 - 0.35 m ² /g	
Fisher Sub Sieve Sizer:	5.5 - 6.5 μm	
Loss on Drying: (1 hour @ 110°C in air)	<0.1%	
Loss on Ignition: (1 hour @ 538°C in air)	<0.1%	
		PSD measured by Microtrac S3000



Ames Goldsmith 4μm 15kv 2.5kx

Released: 08/03

21 Roger Street, Glens Falls, NY 12801
 TEL: (518)-792-5808 FAX: (518)-792-1034
www.amesgoldsmith.com
 Email: sales@amesgoldsmith.com



The statements and data contained herein are considered to be accurate and have been determined by Ames Goldsmith using commonly accepted methods. Ames Goldsmith makes no warranty with respect to the information in whole or in part. The use and application of such information is at the user's own discretion and risk, without any liability on the part of Ames Goldsmith. The physical and chemical data reported is representative of our standard process. Ames Goldsmith has the expertise to modify our processes to provide a product that best suits your application.